

roll covers for the sheet metal industry

→ Sheet metal pre-treatment

Machine position	Compound	Hardness	Features
Pickling, immersion, squeeze, pressure, carrier and guide rolls	7By2 Rubber	50 - 85 ShA	<ul style="list-style-type: none"> • good abrasion and cutting resistance • excellent chemical resistance even to oxidizing media • material not resistant to oil • cover color: black
	7By2 Rubber	75 ShA	<ul style="list-style-type: none"> • special compound for applications under strongly oxidizing conditions • material not resistant to oil • cover color: grey
	7H6 Rubber	55 - 85 ShA	<ul style="list-style-type: none"> • good abrasion and cutting resistance • good chemical resistance • for operation in oxidizing media if oil residues cannot be eliminated • cover color: black
	7P41 Rubber	60 - 80 ShA	<ul style="list-style-type: none"> • excellent abrasion and cutting resistance • good chemical resistance • material not resistant to oxidation • good oil resistance • cover color: red
	8P2 Rubber	55 - 85 ShA	<ul style="list-style-type: none"> • excellent abrasion and cutting resistance • good chemical resistance • material not resistant to oxidation • good oil resistance • cover color: black

These overviews are supposed to give a general idea of what we provide. Different hardness rates are available on application. Surface design/finish, elasticity and functional properties can be designed to any special requirements.